1994-01-01

Cyclic voltammetry of polypyrroledodecylbenzenesulfonate layers

T. McCormac
Technological University Dublin

W. Breen
Technological University Dublin

A. McGee
Technological University Dublin

See next page for additional authors

Follow this and additional works at: <https://arrow.tudublin.ie/scschcpsart>

Part of the [Chemistry Commons](#)

Recommended Citation

McCormac, T., Breen, W., McGee, A., Cassidy, J.F., Lyons, M.E.G.: Cyclic voltammetry of polypyrroledodecylbenzenesulfonate layers. *Electroanalysis*, Vol. 7, 1995, pp.287-289. doi:10.1002/elan.1140070317

This Article is brought to you for free and open access by the School of Chemical and Pharmaceutical Sciences at ARROW@TU Dublin. It has been accepted for inclusion in Articles by an authorized administrator of ARROW@TU Dublin. For more information, please contact arrow.admin@tudublin.ie, aisling.coyne@tudublin.ie, gerard.connolly@tudublin.ie.

Authors

T. McCormac, W. Breen, A. McGee, John Cassidy, and M. E.G. Lyons

Cyclic Voltammetry of Polypyrroledodecylbenzenesulfonate Layers

T. McCormac,⁺ W. Breen,⁺ A. McGee,⁺ J.F. Cassidy⁺ and M.E.G. Lyons⁺⁺

⁺ Chemistry Department, Dublin Institute of Technology, Kevin Street, Dublin 8, Ireland

⁺⁺ Chemistry Department, Trinity College, Dublin 2, Ireland

Received: January 14, 1994

Final version: April 8, 1994

Abstract

Polypyrrole was deposited from solutions of NaClO₄ and NaDBS, where DBS is dodecylbenzenesulfonate, in aqueous solution and characterized by voltammetry. It is found that the absence of the so-called 'double layer charging current' during cyclic voltammetry of the layers formed from solutions with surfactant is not because of the order in morphology of the layer, but irreversible incorporation of the surfactant anion.

Keywords: Polypyrrole, Dodecylbenzenesulfonate, Cyclic voltammetry, Modified electrode.

The electrochemical behavior of conducting polymers has more recently been envisaged in terms of electron transfer between sites within and between chains rather than the metallic-like behavior formerly proposed [1–3]. Transmission line models composed of a resistance due to electron transport along and between chains in parallel with a resistance associated with ionic transport have become popular [4–6]. In general, the resistance due to movement of ions through pores is less than the resistance due to redox conduction of electrons through the layer [3]. The role of morphology of the layer and the nature of charge carrying ions is important in defining the relative values of these two resistance values. Recently the use of larger anions as dopants has been studied [7–10]. Of these, dodecylbenzenesulfonate (DBS) has been shown to exhibit unusual electrochemistry [11] and this article describes some further work on the polypyrroledodecylbenzenesulfonate (PPDBS) layer.

See the Experimental section for details of the procedure followed. It was found [12] that PPDBS layers, when examined under SEM were flat and showed no features, unlike polypyrrole perchlorate, PPClO₄, which displayed a cauliflower-like morphology.

Figure 1 shows the cyclic voltammetry of a layer, previously formed in an aqueous 0.1 mol dm⁻³ LiClO₄/0.1 mol dm⁻³ pyrrole solution, washed in deionized water and transferred to a solution of 0.1 mol dm⁻³ LiClO₄. The characteristic 'double-layer charging-like' behavior can be seen clearly and the current magnitude at the switching potential has previously been used to determine the capacitance of the layer [13]. The broad nature of the voltammetry indicates that the system does not merely consist of a simple surface-confined redox species. Models for this behavior include that of a series of oligomers, each of which has a characteristic formal potential leading to a broad voltammetry [14]. It has also been proposed that the broad voltammetry has been due to electrostatic repulsions between oxidized sites in the polymer [15, 16]. Such a capacitive-like behavior has been seen for polypyrrole, previously formed in solutions of pyrrole and tetrabutylammonium perchlorate, and run in electrolytes such as NaCl, NaNO₃, and has been absent in solutions of Na₂CO₃ and Na₂SO₄ [17].

Figure 2 shows a layer formed in 0.1 mol dm⁻³ NaDBS/0.1 mol dm⁻³ pyrrole and cycled in 0.1 mol dm⁻³ NaClO₄. The voltammograms in Figures 1 and 2 represent the final steady state voltammetry of the layer in the particular electrolyte. It may take 20–30 scans to reach a situation where a steady state voltammetry is seen. Previously it has been reported that

continued cycling causes a greater than equilibrium concentration of electrolyte in the pores for the film [18], which may account for the 'breaking-in' process. The small degree of double layer charging, seen at the switching potential in Figure 2, has been attributed to the ordering of the layer during its formation in the surfactant solution [8, 9, 11]. It can be seen that the predominant ionic movement is that of cations since the peak shifts in a positive direction with increasing electrolyte concentration; this is in common with previous experimental results [19, 20]. If the potential is scanned over a potential region

Fig. 1. Cyclic voltammetry of a layer formed in 0.1 mol dm⁻³ LiClO₄/0.1 mol dm⁻³ pyrrole by scanning continuously between 0.0 and 0.8 V until 20 mC of charge had passed. The layer was then transferred to 0.1 mol dm⁻³ LiClO₄. Scan rate: 50 mV/s, Pt electrode area: 0.0707 cm².

Fig. 2. Cyclic voltammetry of a layer formed in 0.1 mol dm^{-3} NaDBS/ 0.1 mol dm^{-3} pyrrole by scanning continuously between 0 and 0.78 V until 20 mC of charge had passed. The layer was then transferred to NaClO₄ solutions where the concentrations are shown in the figure. Scan rate: 50 mV/s, Pt electrode area: 0.0707 cm^2 .

more positive than -0.2 V , there is very little capacitive-like current which has been reported to be due to the morphology of the layer [11, 19].

Many cyclic voltammetric studies of polypyrrole, formed from a solution of a large anion, are carried out in solutions of either the same anion or smaller anions as electrolyte. In these cases the cation in solution moves in and out during the redox reactions of the layer. In this work a polypyrrole perchlorate layer is cycled in a solution containing sodium dodecylbenzenesulfonate and it was found that the dodecylbenzenesulfonate exchanged into the layer. Figure 3 shows the voltammetry of a layer formed in 0.1 mol dm^{-3} NaClO₄/ 0.1 mol dm^{-3} pyrrole and run in NaDBS. It can be seen that there is a definite change in the electrochemical characteristics of the film when a layer is formed in NaClO₄ and transferred to a surfactant solution. There appears a sharp peak at -0.7 V , similar to, but more negative than that in Figure 2. It can be seen from Figure 3, that despite the size of DBS, it can replace some ClO₄⁻ in the layer. Once DBS has entered into the layer, it is cation movement that defines the ionic mobility as can be seen when the background electrolyte concentration is increased, the peak moves in a positive direction. The DBS irreversibly enters into the layer, since when this electrode was subsequently placed in 0.1 mol dm^{-3} NaClO₄, the DBS did not fully exchange out on cycling. Since the morphology of the layer is determined by the

Fig. 3. Cyclic voltammetry of a layer formed in 0.1 mol dm^{-3} NaClO₄/ 0.1 mol dm^{-3} pyrrole by scanning continuously between 0 and 0.8 V until 20 mC of charge had passed. The layer was then transferred to NaDBS solutions; the concentrations are shown in the figure. Scan rate: 50 mV/s, Pt electrode area: 0.0707 cm^2 .

conditions of its formation, the double layer charging characteristics of Figure 1 is a function of the electrolyte since it has been suppressed in DBS solution. It can be seen, however, that the current magnitude is much less in Figure 3 than in the first two figures indicating that there is only a partial exchange of ClO₄⁻ with DBS. It has been shown elsewhere [21], by probe beam deflection, that Cl⁻ can partially replace dodecylsulfate from a polypyrrole dodecylsulfate layer implying that the movement of large anions out of polypyrrole layers is possible. This is in contrast with previous reports of only cation movement for polypyrrole dodecylsulfate [20, 22, 23] and polypyrrole dodecylbenzenesulfonate [24]. Figure 4 shows a layer formed in a solution of 0.1 mol dm^{-3} NaDBS and 0.1 mol dm^{-3} pyrrole and transferred to a solution of 0.1 mol dm^{-3} LiClO₄. In the ClO₄⁻ solution it can be seen that a peak at negative potentials is characteristic of the movement of cations. However, it can be also seen that there is a peak due to the movement of ClO₄⁻ close to 0.0 V which is not as dominant in NaClO₄ (see Figure 2). This may be because of the greater hydrated radius of Li⁺ which makes its incorporation more difficult. For polypyrrole layers formed with [Fe(CN)₆]⁴⁻ as anions [25], Li⁺ was the most difficult cation of the alkalis to be incorporated, which is also the case for polypyrrole formed in the presence of cupric hexacyanoferrate [26].

It should be noted that the concentration of the surfactant (0.1 M), is above the critical micelle concentration ($1.2 \times 10^{-3} \text{ mol dm}^{-3}$, [27]). It was found that a layer formed in a $1 \times 10^{-3} \text{ mol dm}^{-3}$ NaDBS/ 0.1 mol dm^{-3} pyrrole, which

Fig. 4. Cyclic voltammetry of a layer formed in 0.1 mol dm^{-3} NaDBS/ 0.1 mol dm^{-3} pyrrole by scanning continuously between 0 and 0.8 V until 20 mC charge had passed. The layer was then transferred to LiClO_4 solutions; the concentrations are shown in the figure. Scan rate: 50 mV/s , Pt electrode area: 0.0707 cm^2 .

takes a greater number of scans to form, exhibits identical behavior to that in Figure 4 showing that the layer morphology is not affected by the DBS concentration in the solution in which the PP is formed.

It can be seen that DBS irreversibly enters into PP layers and that electrochemistry is dominated by cation movement. So much so that when a PPClO_4 layer is placed in a DBS solution, the DBS extracts itself into the layer and the electrochemistry on cycling is dominated by cation movement. That the layer electrochemistry is not due to the morphology of the layer can be seen since when a layer formed in ClO_4^- (cauliflower-like morphology, viewed by SEM [12]) is placed in DBS, its electrochemistry is similar to that formed in DBS (which has a flatter morphology viewed by SEM). Therefore the electrochemistry and notably the small 'double layer charging current' is due to the presence of a large anion in solution rather than the polymer morphology as has previously been implied.

Experimental

Sodium dodecylbenzenesulfonate (NaDBS, Aldrich) was technical grade. Pyrrole (Aldrich) was distilled and stored in the dark under nitrogen before use. Water was distilled and deionized. A conventional single compartment three electrode

cell was employed for electrochemistry. The potentiostat consisted of a Sycopel Model DP301, which was linked to a JLLoyd PL3 chart recorder. All potentials are quoted with respect to a calomel electrode in saturated aqueous NaCl. All electrochemistry was carried out at a platinum disk (geometric area: 0.071 cm^2) which was polished with $0.3 \mu\text{m}$ alumina (Leco) on felt prior to use. A carbon rod served as the auxiliary electrode.

Polymer preparation. Polymer layers were formed in aqueous solution by scanning the platinum electrode potential between the limits 0.0 V and +0.8 V and monitoring the charge until a total anodic charge of 20 mC passed.

Acknowledgment

J.C. thanks EOLAS for support from grants ARP/61 and ST/91/001/B.

References

- [1] S. Fletcher, *J. Electroanal. Chem.* 1992, 337, 127.
- [2] X. Ren, P.G. Pickup, *J. Chem. Soc. Faraday Trans.* 1993, 89, 321.
- [3] X. Ren, P.G. Pickup, *J. Electrochem. Soc.* 1992, 139, 2097.
- [4] S. Fletcher, *J. Chem. Soc. Faraday Trans.* 1993, 89, 311.
- [5] W.J. Albery, C.M. Elliott, A.R. Mount, *J. Electroanal. Chem.* 1990, 288, 15.
- [6] W.J. Albery, A.R. Mount, *J. Electroanal. Chem.* 1991, 305, 3.
- [7] J.M. Pernaut, R.C.D. Peres, V.F. Juliano, M.A. De Paoli, *J. Electroanal. Chem.*, 1989, 274, 225.
- [8] L.F. Warren, D.P. Anderson, *J. Electrochem. Soc.* 1987, 134, 101.
- [9] L.F. Warren, J.A. Walker, D.P. Anderson, C.G. Rhodes, L.J. Buckley, *J. Electrochem. Soc.* 1989, 136, 2286.
- [10] X. Ren, P.G. Pickup, *J. Phys. Chem.* 1993, 97, 5356.
- [11] M.E.G. Lyons, W. Breen, J. Cassidy, *J. Chem. Soc. Faraday Trans.* 1991, 87, 115.
- [12] W. Breen, *Ph.D. Thesis*, University of Dublin 1991.
- [13] S. Panero, P. Prosperi, S. Passerini, B. Scrosati, D.P. Perlmuter, *J. Electrochem. Soc.* 1989, 136, 3729.
- [14] J. Heinze, M. Storzach, J. Mortensen, *Ber. Bunsenges. Physikal. Chemie.* 1987, 91, 960.
- [15] M.E.G. Lyons, H.G. Fay, T. McCabe, J. Corish, J.G. Vos, A.J. Kelly, *J. Chem. Soc. Faraday Trans.* 1990, 86, 2905.
- [16] M.E.G. Lyons, H.G. Fay, T. McCabe, *Key Eng. Mater.* 1992, 72/74, 381.
- [17] R. John, G.G. Wallace, *J. Electroanal. Chem.* 1993, 354, 145.
- [18] G.L. Duffitt, P.G. Pickup, *J. Chem. Soc. Faraday Trans.* 1992, 88, 1417.
- [19] M.E.G. Lyons, C.H. Lyons, C. Fitzgerald, T. Bannon, *Analyst* 1993, 118, 361.
- [20] C. Zhong, K. Doblhofer, *Electrochim. Acta* 1990, 35, 1971.
- [21] V.M. Schmidt, C. Barbero, R. Kotz, *J. Electroanal. Chem.* 1993, 352, 301.
- [22] C. Zhong, K. Doblhofer, G. Weinberg, *J. Chem. Soc., Faraday Discuss.* 1989, 88, 307.
- [23] M.A. dePaoli, S. Panero, P. Prosperi, B. Scrosati, *Electrochim. Acta* 1990, 35, 1145.
- [24] M.A. dePaoli, S.C.D. Peres, S. Panero, B. Scrosati, *Electrochim. Acta* 1992, 37, 1173.
- [25] W. Breen, J.F. Cassidy, M.E.G. Lyons, *J. Electroanal. Chem.* 1991, 29, 445.
- [26] Y. Li, W. Zhang, S. Dong, *Electroanalysis* 1993, 5, 431.
- [27] R.J. Hunter, *Zeta Potential in Colloid Science, Principles and Applications*, Academic Press, London 1981.